

Material Characteristics of Laminated Composite Shell

Introduction

This model serves the purpose of validation and verification of the Layered Linear Elastic Material model in the Shell interface.

Analysis of laminated composite shells is commonly based on one of three different theories (Ref. 1),

- I Equivalent Single Layer (ESL) Theory (2D)
 - **a** Classical Laminated Plate Theory (CLPT-ESL)
 - **b** First Order Shear Deformation Laminated Plate Theory (FSDT-ESL)
 - c Higher Order Shear Deformation Laminated Plate Theory
- 2 Three Dimensional Elasticity Theory (3D)
 - a Traditional Three Dimensional Elasticity Theory
 - **b** Layerwise Theory
- 3 Multiple Model Methods (3D and 2D)

In COMSOL Multiphysics, composites are analyzed either based on Layerwise 3D elasticity theory through the Layered Shell interface or based on FSDT-ESL theory through the Shell interface.

The First Order Shear Deformation Theory (FSDT-ESL) is implemented in the **Layered Linear Elastic Material** model in the Shell interface available with the Composite Materials Module. This theory treats a heterogeneous laminated composite as a statically equivalent single layer. ESL theory reduces a 3D continuum problem to an equivalent 2D problem, thus reducing the size and computational time of the problem.

This example is a NAFEMS benchmark, described in *Benchmarks for Membrane and Bending Analysis of Laminated Shells, Part 2: Stiffness Matrix and Thermal Characteristics* (Ref. 2). Membrane and bending stiffness, flexibility matrices, midplane strains in case of unit loading, and the response to a unit change in temperature and unit temperature gradient are verified.

Model Definition

The geometry of the problem consists of eight square layers stacked above each other. The side length is 1 cm and each layer has a thickness of 0.1 mm, as shown in Figure 2. The laminate has $[0/60/-60/0]_s$ stacking sequence as shown in Figure 1.



Figure 1: Stacking sequence $[0/60/-60/0]_s$ from bottom to top, showing fiber orientation in each ply.



Figure 2: Cross-section view of laminated composite shell showing thickness (0.1mm) of each ply.

MATERIAL PROPERTIES

The transversely isotropic material properties (Young's modulus, shear modulus, Poisson's ratio, and thermal expansion coefficients) are given in Table 1:

TABLE I: MATERIAL PROPERTIES.

Material property	Value
$\{E_1, E_2\}$	{213,8.2} GPa
{G ₁₂ }	{3.2} GPa
$\{v_{12}, v_{23}\}$	{0.3,0}
$\{\alpha_1, \alpha_2, \alpha_3\}$	{I.3e-6,27e-6,27e-6} I/K

All material properties are given in the layer coordinate system (local material directions of a layer), where the first axis is aligned with the fiber orientation.

BOUNDARY CONDITIONS

The constraints and loads applied on each node for unit loading and thermal loading are given in the tables below.

Unit load and thermal cases Node	N1	N ₂	N ₁₂	Μ1	M ₂	M ₁₂	ΔΤ/ Τ'
1	$u, v, w, \theta_x, \theta_v, \theta_z$	$u, v, w, \\ \theta_x, \theta_v, \theta_z$	$u, v, w, \\ \theta_{x}, \theta_{v}, \theta_{z}$	$u, v, w, \theta_x, \theta_v, \theta_z$	$ u, v, w, \\ \theta_x, \theta_v, \theta_z $	u, ν, w, θ _v , θ _z	u, ν, w, θ _z
2	u, θ_z	θ_z	ν, θ _z	u, θ_z	θ_z	w, θ_z	u, w, θ_z
3	θ_z	v, θ_z	u, θ_z	$\theta_{\rm z}$	v, θ_z	$\theta_{\rm z}$	w, θ_z
4	$\theta_{\rm z}$	$\theta_{\rm z}$	$\theta_{\rm z}$	$\theta_{\rm z}$	$\theta_{\rm z}$	v, θ_z	$\theta_{\rm z}$

TABLE 2: NODE NUMBERS AND NODAL CONSTRAINTS.

TABLE 3: NODE NUMBERS AND NODAL POINT LOADS, MOMENTS.

Unit load cases	N_1	N ₂	N ₁₂	M_1	M ₂	M ₁₂
Node						
1	0	0	0	$M_v = -5e - 3$	M _x =5e-3	0
2	0	F _y =5e-3	F _x =5e-3	M _y =-5e-3	$M_{x} = -5e - 3$	0
3	F _x =5e-3	0	F _y =5e-3	M _v =5e-3	M _x =5e-3	F _z =2
4	F _x =5e-3	F _y =5e-3	F _x =5e-3 F _y =5e-3	M _y =5e-3	$M_x = -5e - 3$	F _z =-2

Note that the way the benchmark is specified, it is assumed that a single first-order fournode element is used. This is the only case when such a specification can give a homogeneous strain state.

The node numbers specified in the benchmark are equal to the point numbers in the COMSOL Multiphysics geometry. The signs of the point loads and moments are adjusted to give positive unit loads and moments as specified in Ref. 2. The rotation around the *z*-axis, θ_z , is automatically constrained so it does not need to be considered. The unit change in temperature and unit temperature gradient is prescribed using a **Thermal Expansion** subnode of the **Layered Linear Elastic Material**.

Results and Discussion

The results presented in the benchmark (Ref. 2) are for the Classical Laminated Plate Theory (CLPT-ESL). The implementation of Layered Linear Elastic Model is however based on First Order Shear Deformation Theory (FSDT-ESL). The difference between both theories is that FSDT theory considers transverse shear stresses, but for the benchmark example with unit in-plane loading, the results should match between both theories because of the zero or negligible shear strains. Note that the bending strains are actually curvatures, but for consistency purpose they will be called as strains throughout this document.

The relation between in-plane forces and moments with midplane strains is represented by

$$\begin{bmatrix} N \\ M \end{bmatrix} = \begin{bmatrix} A & B \\ B & D \end{bmatrix} \begin{bmatrix} \varepsilon \\ \kappa \end{bmatrix}$$
(1)

where A, B, and D are called *extensional stiffness matrix*, bending-extensional stiffness matrix, and bending stiffness matrix, respectively.

The same relation can be represented on flexibility form as

$$\begin{bmatrix} \varepsilon \\ \kappa \end{bmatrix} = \begin{bmatrix} a & b \\ b & d \end{bmatrix} \begin{bmatrix} N \\ M \end{bmatrix}$$
(2)

where *a*, *b*, and *d* are called *extensional flexibility matrix*, *bending-extensional flexibility matrix*, and *bending flexibility matrix*, respectively. The relationship between stiffness and flexibility matrices is

$$\begin{bmatrix} a & b \\ b & d \end{bmatrix} = \begin{bmatrix} A & B \\ B & D \end{bmatrix}^{-1}$$
(3)

In the benchmark, the laminate flexibility matrix are computed in two ways, first directly from CLPT theory and then from midplane strains when unit loads and moments are applied. When unit in-plane forces N_{ij} and unit moments M_{ij} are applied, the midplane strains and curvature are the elements of flexibility matrix. The midplane strains in the benchmark are computed numerically using commercial finite element software. Table 4 and Table 5 shows the flexibility matrix from the benchmark (Ref. 2).

Strains	N_1	N ₂	N ₁₂	M_1	M_2	M ₁₂
ε ₁	1.131E-8	-3.697E-9	-4.42E-41	-1.59E-21	-3.8E-22	3.27E-21
ϵ_2	-3.69E-9	2.010E-8	1.16E-40	3.977E-22	-8.0E-21	-9.6E-22
γ_{12}	-4.42E-41	1.16E-40	5.593E-8	1.91E-21	-3.0E-21	-1.3E-20
κ ₁	-1.59E-21	-3.8E-22	3.27E-21	1.807E-1	-5.85E-2	-1.42E-3
κ2	3.977E-22	-8.0E-21	-9.6E-22	-5.85E-2	5.17E-1	-3.31E-1
κ ₁₂	1.91E-21	-3.0E-21	-1.3E-20	-1.42E-3	-3.31E-1	I.470E0

TABLE 4: LAMINATE FLEXIBILITY MATRIX BASED ON CLASSICAL LAMINATE PLATE THEORY FROM BENCHMARK

Strains	N_1	N ₂	N ₁₂	M_1	M_2	M_{12}
ε ₁	1.131E-8	-3.697E-9	-3.30E-24	0.00E0	0.00E0	0.00E0
ϵ_2	-3.69E-9	2.010E-8	I.44E-24	0.00E0	0.00E0	0.00E0
γ_{12}	-2.06E-25	-1.65E-24	5.593E-8	0.00E0	0.00E0	0.00E0
κ ₁	0.00E0	0.00E0	0.00E0	1.807E-1	-5.85E-2	-1.42E-3
к ₂	0.00E0	0.00E0	0.00E0	-5.85E-2	5.17E-1	-3.31E-1
κ_{12}	0.00E0	0.00E0	0.00E0	-1.42E-3	-3.31E-1	I.470E0

TABLE 5: LAMINATE FLEXIBILITY MATRIX BASED ON MIDPLANE STRAINS FROM BENCHMARK

The midplane strains for a unit change in temperature are given in the benchmark (Ref. 2)

TABLE 6: MIDPLANE STRAINS FOR UNIT CHANGE IN TEMPERATURE FROM BENCHMARK

Strains	Theory	Numerical FEM
ϵ_1	1.9155E-6	1.9155E-6
ϵ_2	3.4566E-6	3.4566E-6
γ_{12}	0.00E0	-2.117E-22
κ ₁	0.00E0	0.00E0

TABLE 6: MIDPLANE STRAINS FOR UNIT CHANGE IN TEMPERATURE FROM BENCHMARK

Strains	Theory	Numerical FEM
κ_2	0.00E0	0.00E0
κ_{12}	0.00E0	0.00E0

The midplane strains for a unit temperature gradient are given in the benchmark (Ref. 2)

Strains	Theory	Numerical FEM
ε ₁	0.00E0	0.00E0
ϵ_2	0.00E0	0.00E0
γ ₁₂	0.00E0	0.00E0
κ ₁	1.7218E-6	1.7218E-6
κ2	4.8753E-6	4.8753E-6
κ ₁₂	-3.1156E-6	-3.1156E-6

TABLE 7: MIDPLANE STRAINS FOR UNIT TEMPERATURE GRADIENT FROM BENCHMARK

In COMSOL Multiphysics, the stiffness (A, B, D) and flexibility matrices (a, b, d) are available as postprocessing variables. The midplane strains are computed for each unit load cases (six load cases). The strain vector then represents a column in the full flexibility matrix for a unit load case. For example, the membrane and bending midplane strains forms a first column of full flexibility matrix for unit N_1 . The full flexibility matrix based on First Order Shear Deformation Theory (FSDT-ESL) and midplane strains from COMSOL are shown in Table 8 and Table 9 below

Strains	N_1	N_2	N ₁₂	M_1	M_2	M ₁₂
ε ₁	1.131E-8	-3.697E-9	2.27E-25	-4.79E-22	-2.3E-22	-1.0E-21
ϵ_2	-3.69E-9	2.010E-8	7.80E-24	-5.75E-23	I.40E-20	4.47E-20
γ_{12}	2.27E-25	7.80E-24	5.593E-8	-1.27E-21	3.94E-20	1.80E-20
κ1	-4.79E-22	-2.3E-22	-1.0E-21	I.807E-I	-5.85E-2	-1.42E-3
к ₂	-5.75E-23	I.40E-20	4.47E-20	-5.85E-2	5.17E-1	-3.31E-1
κ ₁₂	-1.27E-21	3.94E-20	1.80E-20	-1.42E-3	-3.31E-1	I.470E0

TABLE 8: LAMINATE FLEXIBILITY MATRIX BASED ON FSDT THEORY FROM COMSOL

Strains	N_1	N ₂	N ₁₂	M_1	M_2	M ₁₂
ε ₁	1.131E-8	-3.697E-9	0.00E0	0.00E0	0.00E0	0.00E0
ϵ_2	-3.69E-9	2.010E-8	1.55E-23	0.00E0	0.00E0	0.00E0
γ_{12}	-6.41E-24	1.42E-23	5.593E-8	0.00E0	0.00E0	0.00E0
κ ₁	0.00E0	0.00E0	0.00E0	I.807E-I	-5.85E-2	-1.42E-3
κ ₂	0.00E0	0.00E0	0.00E0	-5.85E-2	5.17E-1	-3.31E-1
κ_{12}	0.00E0	0.00E0	0.00E0	-1.42E-3	-3.31E-1	I.470E0

TABLE 9: LAMINATE FLEXIBILITY MATRIX BASED ON MIDPLANE STRAINS FROM COMSOL

The midplane strains for unit change in temperature and unit temperature gradient from COMSOL are

TABLE 10: MIDPLANE STRAINS FOR UNIT CHANGE IN TEMPERATURE FROM COMSO	TABLE 10:	MIDPLANE STRAI	NS FOR UNIT	CHANGE IN	I TEMPERATURE	FROM COMSOL
--	-----------	----------------	-------------	-----------	---------------	-------------

Strains	COMSOL
ε ₁	1.9155E-6
ε2	3.4566E-6
γ_{12}	-1.645E-21
κ1	-2.371E-19
к ₂	-1.2757E-17
κ_{12}	8.380E-18

TABLE 11: MIDPLANE STRAINS FOR UNIT TEMPERATURE GRADIENT FROM COMSOL

Strains	COMSOL
ε1	6.21611E-26
ϵ_2	-4.60298E-25
γ_{12}	-4.79904E-26
κ ₁	1.72175E-6
κ2	4.87532E-6
κ ₁₂	-3.11557E-6

When comparing Table 4 to Table 8, Table 5 to Table 9, Table 6 to Table 10, and Table 7 to Table 11, an exact match can be found between the results of benchmark model and the results computed in COMSOL Multiphysics. The full flexibility matrix is found by inverting the full stiffness matrix, so the verification of the full flexibility matrix

automatically verifies also the correctness of full stiffness matrix (not presented here but shown in the model).

Notes About the COMSOL Implementation

- Modeling a composite laminated shell requires a surface geometry (2D), in general called a base surface, and a **Layered Material** node which adds an extra dimension (1D) to the base surface geometry in the surface normal direction. In the **Layered Material** node, you can model many layers stacked on top of each other having different thickness, material properties, and fiber orientations. You can also optionally specify the interface materials between the layers and control mesh elements in each layer.
- The Layered Material Link and Layered Material Stack have an option to transform given Layered Material into a symmetric or antisymmetric laminate. A repeated laminate can also be constructed using a transform option.
- From a constitutive equations point of view, you can either use the *Layerwise (LW)* theory based Layered Shell interface, or *Equivalent Single Layer (ESL)* theory based **Layered Linear Elastic Material** node in the Shell interface.
- The six different unit load cases and two thermal loading cases requires different boundary conditions and point loads as shown in Table 2 and Table 3. To solve all these cases in a single study, different load groups and constraint groups are created, and constrains and loads corresponding to a particular case are assigned to these groups according to Table 2 and Table 3. In the Stationary node in the study, appropriate load and constraint groups are selected for each load case.

References

1. J. N. Reddy, *Mechanics of Laminated Composite Plates and Shells: Theory and Analysis, Second Edition, CRC Press, 2004.*

2. P. Hopkins, Benchmarks for Membrane and Bending Analysis of Laminated Shells, Part 1: Stiffness Matrix and Thermal Characteristics, NAFEMS, 2005.

Application Library path: Composite_Materials_Module/ Verification_Examples/laminated_shell_material_characteristics

Modeling Instructions

From the File menu, choose New.

NEW

In the New window, click 🔗 Model Wizard.

MODEL WIZARD

- I In the Model Wizard window, click 间 3D.
- 2 In the Select Physics tree, select Structural Mechanics>Shell (shell).
- 3 Click Add.
- 4 Click \bigcirc Study.
- 5 In the Select Study tree, select General Studies>Stationary.
- 6 Click **M** Done.

GLOBAL DEFINITIONS

Parameters 1

Load the material properties from a file.

- I In the Model Builder window, under Global Definitions click Parameters I.
- 2 In the Settings window for Parameters, locate the Parameters section.
- 3 Click 📂 Load from File.
- **4** Browse to the model's Application Libraries folder and double-click the file laminated_shell_material_characteristics_parameters.txt.

In order to apply unit in-plane forces and moments, as well as unit temperature difference and unit temperature gradient, create separate load and constraint groups.

Load Group for Unit NI

- I In the Model Builder window, right-click Global Definitions and choose Load and Constraint Groups>Load Group.
- 2 In the Settings window for Load Group, type Load Group for Unit N1 in the Label text field.

3 Repeat this five times to get six load groups. Rename them as shown in the table below.

Name	Label
Load Group 2	Load Group for Unit N2
Load Group 3	Load Group for Unit N12
Load Group 4	Load Group for Unit M1
Load Group 5	Load Group for Unit M2
Load Group 6	Load Group for Unit M12

4 Select all load groups and right click on **Group** to create a group.

Load Groups for Unit Loading

- I In the Model Builder window, under Global Definitions>Load and Constraint Groups click Group I.
- 2 In the Settings window for Group, type Load Groups for Unit Loading in the Label text field.

Load Group for Unit Temperature Difference

- I In the Model Builder window, right-click Load and Constraint Groups and choose Load Group.
- 2 In the Settings window for Load Group, type Load Group for Unit Temperature Difference in the Label text field.

Load Group for Unit Temperature Gradient

- I Right-click Load and Constraint Groups and choose Load Group.
- 2 In the Settings window for Load Group, type Load Group for Unit Temperature Gradient in the Label text field.
- **3** Select thermal load groups and right click on **Group** to create a group.

Load Groups for Thermal Loading

- I In the Model Builder window, under Global Definitions>Load and Constraint Groups click Group 2.
- 2 In the Settings window for Group, type Load Groups for Thermal Loading in the Label text field.

Constraint Group for Unit NI, N2, NI2, MI and M2

I In the Model Builder window, right-click Load and Constraint Groups and choose Constraint Group.

- 2 In the Settings window for Constraint Group, type Constraint Group for Unit N1, N2, N12, M1 and M2 in the Label text field.
- **3** Repeat this four times to get required numbers of constraint groups. Rename them as shown in the table below.

Name	Label
Constraint Group 2	Constraint Group for Unit N1 and M1
Constraint Group 3	Constraint Group for Unit N2 and M2
Constraint Group 4	Constraint Group for Unit N12
Constraint Group 5	Constraint Group for Unit M12

4 Select all constraint groups and right click on **Group** to create a group.

Constraint Groups for Unit Loading

- I In the Model Builder window, under Global Definitions>Load and Constraint Groups click Group 3.
- 2 In the Settings window for Group, type Constraint Groups for Unit Loading in the Label text field.

Constraint Group for Thermal Loading

- I In the Model Builder window, right-click Load and Constraint Groups and choose Constraint Group.
- 2 In the Settings window for Constraint Group, type Constraint Group for Thermal Loading in the Label text field.

Material I (mat1)

In the Model Builder window, under Global Definitions right-click Materials and choose Blank Material.

Now add a **Layered Material** node and assign appropriate thickness and rotation angles to each layer. The laminate is symmetric. It is sufficient to define only half the laminate in the **Layered Material** node. The transformation into a full laminate is performed through the layered material settings in the **Layered Material Link** node.

Layered Material: [0/60/-60/0]_s

- I Right-click Materials and choose Layered Material.
- 2 In the Settings window for Layered Material, locate the Layer Definition section.

3 In the table, enter the following settings:

Layer	Material	Rotation (deg)	Thickness	Mesh elements
Layer 1	Material I (matI)	0	th	1

4 Click Add three times.

5 In the table, enter the following settings:

Layer	Material	Rotation (deg)	Thickness	Mesh elements
Layer 2	Material I (matI)	60	th	1
Layer 3	Material I (matI)	-60	th	1
Layer 4	Material I (matI)	0	th	1

6 In the Label text field, type Layered Material: [0/60/-60/0]_s.

GEOMETRY I

Work Plane I (wp1)

In the Geometry toolbar, click 😓 Work Plane.

Work Plane I (wpI)>Plane Geometry

In the Model Builder window, click Plane Geometry.

Work Plane 1 (wp1)>Square 1 (sq1)

- I In the Work Plane toolbar, click Square.
- 2 In the Settings window for Square, locate the Size section.
- 3 In the Side length text field, type 1e-2.
- 4 Click 틤 Build Selected.

5 Click the \longleftrightarrow **Zoom Extents** button in the **Graphics** toolbar.

MATERIALS

Layered Material Link 1 (Ilmat1)

I In the Model Builder window, under Component I (comp1) right-click Materials and choose Layers>Layered Material Link.

The half laminate defined in the **Layered Material** node can be transformed into a full symmetric laminate using a transform option in the layered material settings.

2 In the Settings window for Layered Material Link, locate the Layered Material Settings section.

- 3 From the Transform list, choose Symmetric.
- 4 Click to expand the **Preview Plot Settings** section. In the **Thickness-to-width ratio** text field, type 0.5.
- **5** Locate the **Layered Material Settings** section. Click **Layer Cross-Section Preview** in the upper-right corner of the section.
- **6** Click **Layer Stack Preview** in the upper-right corner of the **Layered Material Settings** section.

The geometry is in an XY-plane in which the fibers are oriented with respect to the X direction. Hence set the first axis of the laminate coordinate system in the X direction.

DEFINITIONS (COMPI)

Boundary System 1 (sys1)

- I In the Model Builder window, expand the Component I (comp1)>Definitions node, then click Boundary System I (sys1).
- 2 In the Settings window for Boundary System, locate the Settings section.
- 3 Find the Coordinate names subsection. From the Axis list, choose x.

SHELL (SHELL)

- I Click the 🐱 Show More Options button in the Model Builder toolbar.
- 2 In the Show More Options dialog box, in the tree, select the check box for the node Physics>Advanced Physics Options.
- 3 Click OK.

Set the discretization for the displacement field to **Linear** in order to resemble the benchmark example.

- 4 In the Model Builder window, under Component I (compl) click Shell (shell).
- 5 In the Settings window for Shell, click to expand the Discretization section.
- 6 From the Displacement field list, choose Linear.

Layered Linear Elastic Material I

- I In the **Physics** toolbar, click **m** Boundaries and choose Layered Linear Elastic Material. In order to study two thermal load cases separately, add two **Thermal Expansion** subfeatures and activate them in different load groups.
- **2** Select Boundary 1 only.
- **3** In the **Settings** window for **Layered Linear Elastic Material**, locate the **Linear Elastic Material** section.

- 4 From the Material symmetry list, choose Orthotropic.
- 5 Select the Transversely isotropic check box.

Thermal Expansion for Unit Temperature Difference

- I In the Physics toolbar, click 🧮 Attributes and choose Thermal Expansion.
- 2 In the Settings window for Thermal Expansion, type Thermal Expansion for Unit Temperature Difference in the Label text field.
- 3 Locate the Model Input section. From the *T* list, choose User defined. In the associated text field, type 293.15[K] +1[K].
- 4 In the Physics toolbar, click 🙀 Load Group and choose Load Group for Unit Temperature Difference.

Layered Linear Elastic Material I

In the Model Builder window, click Layered Linear Elastic Material I.

Thermal Expansion for Unit Temperature Gradient

- I In the Physics toolbar, click 📃 Attributes and choose Thermal Expansion.
- 2 In the Settings window for Thermal Expansion, type Thermal Expansion for Unit Temperature Gradient in the Label text field.
- 3 Locate the Thermal Bending section. From the list, choose Temperature gradient in thickness direction.
- **4** In the T' text field, type 1[K/m].
- 5 In the Physics toolbar, click 🙀 Load Group and choose

Load Group for Unit Temperature Gradient.

GLOBAL DEFINITIONS

Material I (mat1)

- I In the Model Builder window, under Global Definitions>Materials click Material I (mat1).
- 2 In the Settings window for Material, locate the Material Contents section.
- **3** In the table, enter the following settings:

Property	Variable	Value	Unit	Property group
Young's modulus	{Evect1, Evect2}	{E1, E2}	Pa	Transversely isotropic
Poisson's ratio	{nuvect1, nuvect2}	{nu12, nu23}	1	Transversely isotropic
Shear modulus	GvectI	{G}	N/m²	Transversely isotropic

Property	Variable	Value	Unit	Property group
Density	rho	1	kg/m³	Basic
Coefficient of thermal expansion	{alphall, alpha22, alpha33}; alphaij = 0	{alpha1, alpha2, alpha3}	I/K	Basic

Apply different constraints and point loads for different load cases as shown in Table 2 and Table 3. Attach appropriate load and constraint groups to these constraints and load features.

SHELL (SHELL)

Fixed Constraint for Unit N1, N2, N12, M1 and M2

- I In the Physics toolbar, click 📄 Points and choose Fixed Constraint.
- 2 In the Settings window for Fixed Constraint, type Fixed Constraint for Unit N1, N2, N12, M1 and M2 in the Label text field.
- 3 Select Point 1 only.
- 4 In the Physics toolbar, click (•) Constraint Group and choose Constraint Group for Unit NI, N2, N12, MI and M2.

Prescribed Displacement/Rotation for Unit NI and MI

- I In the Physics toolbar, click 📄 Points and choose Prescribed Displacement/Rotation.
- 2 In the Settings window for Prescribed Displacement/Rotation, type Prescribed Displacement/Rotation for Unit N1 and M1 in the Label text field.
- 3 Select Point 2 only.
- **4** Locate the **Prescribed Displacement** section. Select the **Prescribed in x direction** check box.
- 5 In the Physics toolbar, click (
 Constraint Group and choose Constraint Group for Unit NI and MI.

6 Duplicate the **Prescribed Displacement/Rotation I** node nine times to get required numbers of nodal constraints. Label, selection, constraints, constraint groups should be as shown in table below.

Name	Label	Selection	DOFs to be constrained	Constraint group
Prescribed Displacement/ Rotation 2	Prescribed Displacement/ Rotation for Unit N2 and M2	3	v	Constraint Group for N2 and M2
Prescribed Displacement/ Rotation 3	Prescribed Displacement/ Rotation for Unit N12 (1)	2	u, v	Constraint Group for N12
Prescribed Displacement/ Rotation 4	Prescribed Displacement/ Rotation for Unit N12 (2)	3	u	Constraint Group for N12
Prescribed Displacement/ Rotation 5	Prescribed Displacement/ Rotation for Unit M12 (1)	1	u, v, w, theta_y	Constraint Group for M12
Prescribed Displacement/ Rotation 6	Prescribed Displacement/ Rotation for Unit M12 (2)	4	v	Constraint Group for M12
Prescribed Displacement/ Rotation 7	Prescribed Displacement/ Rotation for Unit M12 (3)	2	W	Constraint Group for M12
Prescribed Displacement/ Rotation 8	Prescribed Displacement/ Rotation for Unit Change in Temperature (1)	I	u, v, w	Constraint Group for Thermal Loading

Name	Label	Selection	DOFs to be constrained	Constraint group
Prescribed Displacement/ Rotation 9	Prescribed Displacement/ Rotation for Unit Change in Temperature (2)	3	W	Constraint Group for Thermal Loading
Prescribed Displacement/ Rotation 10	Prescribed Displacement/ Rotation for Unit Change in Temperature (3)	2	u, w	Constraint Group for Thermal Loading

Point Load for Unit NI

- I In the Physics toolbar, click 🗁 Points and choose Point Load.
- 2 In the Settings window for Point Load, type Point Load for Unit N1 in the Label text field.
- **3** Select Points 3 and 4 only.
- 4 Locate the Force section. Specify the \mathbf{F}_{P} vector as

Fi	x
0	у
0	z

- 5 In the Physics toolbar, click 🙀 Load Group and choose Load Group for Unit NI.
- 6 Duplicate the **Point Load I** node nine times to get required numbers of nodal loads. Label, selection, loads, load groups should be as shown in the table below.

Name	Label	Selection	Loads/Moments	Load group
Point Load 2	Point Load for Unit N2	2, 4	F_y = Fi	Load Group for N2
Point Load 3	Point Load for Unit N12 (1)	2, 4	F_x = Fi	Load Group for N12
Point Load 4	Point Load for Unit N12 (2)	3, 4	F_y = Fi	Load Group for N12

Name	Label	Selection	Loads/Moments	Load group
Point Load 5	Point Load for Unit M1 (1)	1, 2	M_y = -M	Load Group for M1
Point Load 6	Point Load for Unit M1 (2)	3, 4	M_y = M	Load Group for M1
Point Load 7	Point Load for Unit M2 (1)	1, 3	$M_x = M$	Load Group for M2
Point Load 8	Point Load for Unit M2 (2)	2, 4	$M_x = -M$	Load Group for unit M2
Point Load 9	Point Load for Unit M12 (1)	3	F_z = Fo	Load Group for Unit M12
Point Load 10	Point Load for Unit M12 (2)	4	F_z = -Fo	Load Group for Unit M12

MESH I

Use a single quadrilateral element.

Mapped I

- I In the Mesh toolbar, click A Boundary and choose Mapped.
- 2 In the Settings window for Mapped, locate the Boundary Selection section.
- 3 From the Selection list, choose All boundaries.

Distribution I

- I Right-click Mapped I and choose Distribution.
- 2 In the Settings window for Distribution, locate the Edge Selection section.
- **3** From the **Selection** list, choose **All edges**.
- **4** Locate the **Distribution** section. In the **Number of elements** text field, type **1**.
- 5 Click 📗 Build All.

Create eight different load cases each for six unit loads/moments and two for thermal loading. Assign appropriate load groups and constraint groups for each load cases as per Table 2 and Table 3.

STUDY I

Disable the default plots for this study.

- I In the Model Builder window, click Study I.
- 2 In the Settings window for Study, locate the Study Settings section.
- **3** Clear the **Generate default plots** check box.

Step 1: Stationary

- I In the Model Builder window, under Study I click Step I: Stationary.
- 2 In the Settings window for Stationary, click to expand the Study Extensions section.
- 3 Select the Define load cases check box.
- 4 Click + Add seven times.

5 In the table, select the load cases and select appropriate load and constraint groups.

Load case	Active load groups and constraint groups
Load case for unit N1	lg1 cg1 cg2
Load case for unit N2	lg2 cg1 cg3
Load case for unit N12	lg3 cg1 cg4
Load case for unit M1	lg4 cg1 cg2
Load case for unit M2	lg5 cg1 cg3
Load case for unit M12	lg6 cg5
Load case for unit change in temperature	1g7 cg6
Load case for unit temperature gradient	1g8 cg6

6 In the Home toolbar, click **=** Compute.

In order to find the laminate flexibility and stiffness matrices, use **Point Matrix Evaluation** node under **Evaluation Group**.

RESULTS

Extensional Flexibility Matrix

- I In the Results toolbar, click **Evaluation Group**.
- 2 In the Settings window for Evaluation Group, locate the Data section.
- 3 From the Parameter selection (Load case) list, choose First.
- 4 Click to expand the Format section. From the Include parameters list, choose Off.
- 5 In the Label text field, type Extensional Flexibility Matrix.

Point Matrix Evaluation 1

- I In the Extensional Flexibility Matrix toolbar, click ^{8,85}_{e-12} More Evaluations and choose Point Matrix Evaluation.
- 2 Select Point 3 only.
- 3 In the Settings window for Point Matrix Evaluation, click Replace Expression in the upperright corner of the Expression section. From the menu, choose Component I (compl)> Shell>Stiffness and flexibility>Extensional flexibility matrix>shell.Da -Extensional flexibility matrix - s²/kg.

Extensional Flexibility Matrix

I In the Model Builder window, click Extensional Flexibility Matrix.

2 In the Extensional Flexibility Matrix toolbar, click **=** Evaluate.

TABLE

- I Go to the Table window.
- 2 To compute the remaining flexibility and stiffness matrices, duplicate the above node seven times and change the expression to compute shell.Db, shell.Dd, shell.Das, shell.DA, shell.DB, shell.DD and shell.DAs.

Use a **Point Evaluation** node under **Evaluation Group** to compute the midplane strains for each load case. The choice of point does not matter as the model gives a uniform strain field.

While evaluating the midplane strains corresponding to each load case, evaluate the corresponding in-plane force or moment postprocessing variable in order to verify the correctness of the applied forces and constraints.

RESULTS

Layered Material I

In the **Results** toolbar, click **More Datasets** and choose **Layered Material**.

Cut Point 3D 1

- I In the **Results** toolbar, click **Cut Point 3D**.
- 2 In the Settings window for Cut Point 3D, locate the Data section.
- 3 From the Dataset list, choose Layered Material I.
- 4 Locate the **Point Data** section. In the **x** text field, type 1e-2.
- **5** In the **y** text field, type **0**.
- **6** In the **z** text field, type **0**.

Midplane Strains for Unit NI

- 2 In the Settings window for Evaluation Group, type Midplane Strains for Unit N1 in the Label text field.
- 3 Locate the Data section. From the Dataset list, choose Cut Point 3D I.
- 4 From the Parameter selection (Load case) list, choose From list.
- 5 In the Load cases list, select Load case for unit NI.
- 6 Locate the Format section. From the Include parameters list, choose Off.

Point Evaluation 1

- I Right-click Midplane Strains for Unit NI and choose Point Evaluation.
- 2 In the Settings window for Point Evaluation, locate the Expressions section.
- **3** In the table, enter the following settings:

Expression	Unit	Description
shell.eml11	1	Membrane part of strain tensor (local), 11 component
shell.eml22	1	Membrane part of strain tensor (local), 22 component
2*shell.eml12	1	Membrane part of strain tensor (local), 12 component
shell.ebl11	1/m	Bending part of strain tensor (local), 11 component
shell.ebl22	1/m	Bending part of strain tensor (local), 22 component
2*shell.ebl12	1/m	Bending part of strain tensor (local), 12 component
shell.Nl11	N/m	Local in-plane force, 11 component

Midplane Strains for Unit NI

- I In the Model Builder window, click Midplane Strains for Unit NI.
- 2 In the Midplane Strains for Unit NI toolbar, click **=** Evaluate.

TABLE

- I Go to the **Table** window.
- 2 To compute the midplane strains for remaining load cases, duplicate the above node seven times and change the load case in the **Data** section of corresponding **Evaluation**

Group node. Replace the in-plane force/moment variable in the last row of table in **Point Evaluation** node with appropriate variable corresponding to the load cases.

24 | MATERIAL CHARACTERISTICS OF LAMINATED COMPOSITE SHELL